

Sputtering Al on Si using Sputter#4

Sputtering Condition: 5mT, 200W, Ar=45sccm, z=2.75, tilting=5, and time=30 minutes

Result: the sputtering rate=4.4nm/min.

Figure 1 Al Film Profile

